

<b>DATA SHEET</b>			
<b>QuickSilver®</b>			
Property	Units	Test Method	Typical Average Values
<b>Mechanical</b>			
Specific Gravity, 73° F	-	ASTM D792	.93
Tensile Strength, 73° F	psi	ASTM D638	4400
Tensile Modulus of Elasticity, 73° F	psi	ASTM D638	70000
Tensile Elongation (at break), 73° F	%	ASTM D638	230
Flexural Strength, 73° F	psi	ASTM D790	3500
Flexural Modulus of Elasticity, 73° F	psi	ASTM D790	66000
Shear Strength, 73° F	psi	ASTM D732	4800
Compressive Strength, 10% Deformation, 73° F	psi	ASTM D695	3000
Compressive Modulus of Elasticity, 73° F	psi	ASTM D695	80000
Hardness, Rockwell, Scale as noted, 73° F	-	ASTM D785	N/A
Hardness, Durometer, Shore "D" Scale, 73° F	-	ASTM D2240	66
Izod Impact (notched), 73° F	ft.lb./in.	ASTM D256 Type "A"	No Break
Coefficient of Friction (Dry vs. Steel) Dynamic	-	QTM 55007	.09
Limiting PV (with 4:1 safety factor applied)	ft.lbs.in. <sup>2</sup> min.	QTM 55007	2000
Sand Slurry Abrasion	1018 Steel = 100.	ASTM D4020	10
<b>Thermal</b>			
Coefficient of Linear Thermal Expansion (-40°F to 300°F)	in./in./°F	ASTM E-831 (TMA)	1.1 X 10 <sup>-4</sup>
Heat Deflection Temperature 264 psi	°F	ASTM D648	116
Tg-Glass Transition (amorphous)	°F	ASTM D3418	N/A
Melting Point (crystalline) peak	°F	ASTM D3418	275
Continuous Service Temperature in Air (Max.)(1)	°F	-	180
Thermal Conductivity	BTU in./(hr.ft. <sup>2</sup> °F)	-	N/A

<b>DATA SHEET</b>			
<b>QuickSilver®</b>			
<b>Property</b>	<b>Units</b>	<b>Test Method</b>	<b>Typical Average Values</b>
<b>Electrical</b>			
Dielectric Strength, Short Term	KV/CM	ASTM D149	900
Surface Resistivity	ohms/square	EOS/ESD S11.11	> 10 <sup>13</sup>
Dielectric Constant, 10 <sup>6</sup> Hz	-	ASTM D150	2.3
Dissipation Factor, 10 <sup>6</sup> Hz	-	ASTM D150	< 0.5 X 10 <sup>3</sup>
Flammability @ 3.1 mm (1/8 in.) (3)	-	UL94	HB
<b>Miscellaneous</b>			
Water Absorption Immersion, 24 Hours	% by wt.	ASTM D570(2)	< 0.01
Water Absorption Immersion, Saturation	% by wt.	ASTM D570(2)	< 0.01

- (1) Data represent Quadrant's estimated maximum long-term service temperature based on practical field experience.
- (2) Specimens: 1/8" thick x 2" diameter or square.
- (3) **Estimated rating based on available data.** The UL 94 Test is a laboratory test and does not relate to actual fire hazard. Contact Quadrant for specific UL "Yellow Card" recognition number.