

DATA SHEET			
QuickSilver®			
Property	Units	Test Method	Typical Average Values
Mechanical			
Specific Gravity, 73° F	-	ASTM D792	.93
Tensile Strength, 73° F	psi	ASTM D638	4400
Tensile Modulus of Elasticity, 73° F	psi	ASTM D638	70000
Tensile Elongation (at break), 73° F	%	ASTM D638	230
Flexural Strength, 73° F	psi	ASTM D790	3500
Flexural Modulus of Elasticity, 73° F	psi	ASTM D790	66000
Shear Strength, 73° F	psi	ASTM D732	4800
Compressive Strength, 10% Deformation, 73° F	psi	ASTM D695	3000
Compressive Modulus of Elasticity, 73° F	psi	ASTM D695	80000
Hardness, Rockwell, Scale as noted, 73° F	-	ASTM D785	N/A
Hardness, Durometer, Shore "D" Scale, 73° F	-	ASTM D2240	66
Izod Impact (notched), 73° F	ft.lb./in.	ASTM D256 Type "A"	No Break
Coefficient of Friction (Dry vs. Steel) Dynamic	-	QTM 55007	.09
Limiting PV (with 4:1 safety factor applied)	ft.lbs.in. ² min.	QTM 55007	2000
Sand Slurry Abrasion	1018 Steel = 100.	ASTM D4020	10
Thermal			
Coefficient of Linear Thermal Expansion (-40°F to 300°F)	in./in./°F	ASTM E-831 (TMA)	1.1 X 10 ⁻⁴
Heat Deflection Temperature 264 psi	°F	ASTM D648	116
Tg-Glass Transition (amorphous)	°F	ASTM D3418	N/A
Melting Point (crystalline) peak	°F	ASTM D3418	275
Continuous Service Temperature in Air (Max.)(1)	°F	-	180
Thermal Conductivity	BTU in./(hr.ft. ² °F)	-	N/A

DATA SHEET			
QuickSilver®			
Property	Units	Test Method	Typical Average Values
Electrical			
Dielectric Strength, Short Term	KV/CM	ASTM D149	900
Surface Resistivity	ohms/square	EOS/ESD S11.11	$> 10^{13}$
Dielectric Constant, 10^6 Hz	-	ASTM D150	2.3
Dissipation Factor, 10^6 Hz	-	ASTM D150	$< 0.5 \times 10^3$
Flammability @ 3.1 mm (1/8 in.) (3)	-	UL94	HB
Miscellaneous			
Water Absorption Immersion, 24 Hours	% by wt.	ASTM D570(2)	< 0.01
Water Absorption Immersion, Saturation	% by wt.	ASTM D570(2)	< 0.01

- (1) Data represent Quadrant's estimated maximum long-term service temperature based on practical field experience.
- (2) Specimens: 1/8" thick x 2" diameter or square.
- (3) **Estimated rating based on available data.** The UL 94 Test is a laboratory test and does not relate to actual fire hazard. Contact Quadrant for specific UL "Yellow Card" recognition number.